

## Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended) A stent comprising a coating based on a polymer of hyaluronic acid characterized in that the ~~said~~-hyaluronic acid polymer is an ester derivative of hyaluronic acid, ~~and~~

wherein the ester derivative of hyaluronic acid is not sulfated and

wherein the hyaluronic acid ester derivative has all or some of the carboxyl groups of the hyaluronic acid esterified with alcohols selected from those of the aliphatic, arylaliphatic, cycloaliphatic and heterocyclic series and wherein the degree of esterification of the hyaluronic acid ester derivative varies from 50% to 100% of the carboxyl groups in the hyaluronic acid.

2. (Canceled)

3. (Currently amended) A stent according to claim-~~2~~ 1, in which:

when the ~~said~~-alcohols are of the aliphatic series they are selected from straight or branched saturated or unsaturated alcohols having from 2 to 12 carbon atoms, optionally substituted with one or more groups selected from hydroxide, amine, aldehyde, mercaptan or carboxyl groups or groups derived from these such as for example esters, ethers, acetals, ketals, thioethers, thioesters, carbamides; in particular when the ~~said~~-alcohols are saturated aliphatic alcohols they are selected from methyl, ethyl, propyl, isopropyl, normal butyl, isobutyl, ter-butyl, amyl or pentyl alcohols; when the ~~said~~-alcohols are bivalent aliphatic alcohols they are selected from the alcohols ethylene glycol, propylene glycol, butylene glycol, and when the alcohol is a trivalent aliphatic alcohol it is preferably glycerine; when the ~~said~~-alcohols are amino alcohols, they are selected from aminoethanol, aminopropanol, aminobutanol and their dimethylene- or diethyleneamine derivatives, piperidine ethanol, pyrrolidine ethanol or piperazine ethanol; when the ~~said~~-alcohols are carboxy alcohols, they are selected from lactic, tartaric, maleic or glycolic acids; when the ~~said~~-alcohols are unsaturated aliphatic alcohols they are preferably allyl alcohol

when the ~~said~~-alcohols are of the arylaliphatic series they are selected from those having a benzene optionally substituted with from 1 to 3 methyls or hydroxyls or halogen atoms, in particular fluorine, chlorine, bromine and iodine, and in which the aliphatic chain has from 1 to 4 carbon atoms and is optionally substituted by one or more groups selected from primary amine groups, mono- or dimethylated groups or from pyrrolidine or piperidine groups, in particular they are benzyl alcohol or phenylethyl alcohol,

when the ~~said~~-alcohols are of the cycloaliphatic series they are selected from those mono- or polycyclic alcohols containing from 3 to 34 carbon atoms and optionally containing from 1 to 3 hetero atoms selected from O, S, N and optionally substituted with one or more groups selected from hydroxyl, amine, aldehyde, mercaptan or carboxyl groups or groups derived from these such as for example esters, ethers, acetals, ketals, thioethers, thioesters, carbamides; in particular when the ~~said~~-cycloaliphatic alcohols are monocyclic they are selected from those containing from 5 to 7 carbon atoms, optionally substituted with one or more groups selected from hydroxyl, methyl, ethyl, propyl, isopropyl, and in particular they are cyclohexanol, cyclohexandiol, inositol or menthol.

4. (Canceled)

5. (Currently amended) A stent according to claim-4 1, in which the degree of esterification varies from 70% to 100% of the carboxyl groups in the hyaluronic acid.

6. (Original) A stent according to claim 1, in which the alcohol is benzyl alcohol and the degree of esterification is equal to 100% of the carboxyl groups in the hyaluronic acid.

7. (Original) A stent according to claim 1, in which the alcohol is benzyl alcohol and the degree of esterification is equal to 75% of the carboxyl groups in the hyaluronic acid.

8. (Currently amended) A stent according to claim 1, in which a pharmacologically active ingredient is associated with the ~~said~~-hyaluronic acid polymer coating.

9. (Currently amended) A stent according to claim 8 in which the ~~said~~ active ingredient associated with the ~~said~~ hyaluronic acid polymer coating is selected from the group consisting of active ingredients having an anti-inflammatory, antiproliferative, ~~or~~ antimigratory action, and/or immunosuppressants, and antimigratory and immunosuppressant action.

10. (Currently amended) A stent according to claim 8 in which the ~~said~~ active ingredient is 4-[(4-methyl-1-piperazinyl)methyl]-N-[4-methyl-3-[[4-(3-pyridinyl)-2-pyrimidinyl]amino]-phenyl]benzamide methane sulphonate.

11. (Original) A stent according to claim 9, in which when the active ingredient is an active ingredient having an anti-inflammatory action it is associated with the hyaluronic acid polymer coating in a quantity of between 0.001 mg and 10 mg.

12. (Original) A stent according to claim 9, in which when the active ingredient is an active ingredient having an anti-proliferative action it is associated with the hyaluronic acid polymer coating in a quantity of between 0.0001 mg and 10 mg.

13. (Original) A stent according to claim 9, in which when the active ingredient is an active ingredient having an anti-migratory action it is associated with the hyaluronic acid polymer coating in a quantity of between 0.0001 mg and 10 mg.

14. (Original) A stent according to claim 9, in which when the active ingredient is an immunosuppressant it is associated with the hyaluronic acid polymer coating in a quantity of between 0.0001 mg and 10 mg.

15. (Original) A stent according to claim 10, in which when the active ingredient is 4-[(4-methyl-1-piperazinyl)methyl]-N-[4-methyl-3-[[4-(3-pyridinyl)-2-pyrimidinyl]amino]-phenyl]benzamide methane sulphonate, this is associated with the hyaluronic acid polymer coating in a quantity of between 0.001 mg and 10 mg.

16. (Original) A stent according to claim 1, in which the thickness of the hyaluronic acid polymer coating on the stent varies from 0.5 microns to 40 microns, preferably between 1 and 30 microns, even more preferably between 5 and 10 microns.
17. (Previously presented) A stent according to claim 8, in which the active ingredient and the hyaluronic acid are released from the hyaluronic acid polymer coating over a prolonged time.
18. (Previously presented) A stent according to claim 17, in which the active ingredient and the hyaluronic acid are released from the hyaluronic acid polymer coating in a time exceeding one month.
19. (Previously presented) A stent according to claim 18, in which the active ingredient and the hyaluronic acid are released from the hyaluronic acid polymer coating within two weeks.
20. (Original) A stent comprising a layer of hyaluronic acid covalently bound to the surface of the stent itself and a coating of hyaluronic acid polymer as described in claim 1.
21. (Original) A stent according to claim 1, further comprising a second coating of a polymer having a hydrophobic nature with which a pharmacologically active ingredient is associated.
22. (Currently amended) A stent according to claim 21 in which the ~~said~~ polymer coating having a hydrophobic nature is applied directly to the surface of the stent, beneath the ~~said~~ coating based on hyaluronic acid ester polymer.
23. (Currently amended) A stent according to claim 21, in which the ~~said~~ polymer having a hydrophobic nature has a contact angle with water which is greater than 60°.

24. (Currently amended) A stent according to claim 23 in which the ~~said~~-polymer having a hydrophobic nature is selected from polymethyl methacrylate, polybutyl methacrylate, polyisobutylmethacrylate, olefinic polymers, polybutadiene, polyisoprene, poly(acrylonitrile-butadiene-styrene) or polyvinyl acetate.
25. (Currently amended) A stent according to claim 23 in which the ~~said~~-polymer of a hydrophobic nature is polystyrene.
26. (Currently amended) A stent according to claim 21, in which the ~~said~~-active ingredient associated with the ~~said~~-polymer coating of a hydrophobic nature is selected from active ingredients having an anti-inflammatory, antiproliferative or antimigratory action and/or immunosuppressants.
27. (Currently amended) A stent according to claim 21, in which the ~~said~~-active ingredient associated with the ~~said~~-polymer coating of a hydrophobic nature is 4-[(4-methyl-1-piperazinyl)methyl]-N-[4-methyl-3-[[4-(3-pyridinyl)-2-pyrimidinyl]amino]-phenyl]benzamide methane sulphonate.
28. (Currently amended) A stent according to claim 21, in which the quantity of the ~~said~~-active ingredient associated with the ~~said~~-polymer coating of a hydrophobic nature is between 0.0001 mg and 10 mg.
29. (Currently amended) A stent according to claim 21, in which the thickness of the ~~said~~ polymer coating of a hydrophobic nature on the stent varies from 0.5 microns to 40 microns, preferably between 1 and 30 microns, even more preferably between 5 and 10 microns.
30. (Currently amended) A stent according to claim 21, in which the ~~said~~-active ingredient is released from the ~~said~~-polymer coating of a hydrophobic nature in a time of one month.

31. (Currently amended) A stent according to claim 21, in which the active ingredient and the quantity of active ingredient associated with the ~~said~~-two polymer coatings respectively is the same or different.

32. (Currently amended) A stent according to claim 21, which further includes a layer of hyaluronic acid covalently bound to the ~~said~~-polymer coating of a hydrophobic nature.

33. (Withdrawn) A process for obtaining a coated stent comprising the stages of:  
dissolving the hyaluronic acid ester and the active ingredient in the same organic solvent to obtain a solution,  
immersing and then removing the stent in the said-solution, and  
removing the solvent by evaporation.

34. (Withdrawn) A process according to claim 33 in which the said organic solvent is a dipolar aprotic solvent.

35. (Withdrawn) A process according to claim 34, in which the said-organic solvent is selected from dimethyl sulphoxide, N-methylpyrrolidone, dimethylformamide or hexafluoroisopropanol.

36. (Withdrawn) A process according to claim 33, comprising a stage of pre-treatment of the surface of the stent to which a layer of covalently bound hyaluronic acid is applied.

37. (Withdrawn) A process according to claim 33 in which the said stages a), b), c) are preceded by the following stages in order:

- a1) dissolving the polymer of a hydrophobic nature and the active ingredient in the same organic solvent to obtain a solution or a suspension,
- b1) immersing and then removing the stent in the said solution or suspension, and
- c1) removing the solvent by evaporation.

38. (Withdrawn) A process according to claim 37 in which the said organic solvent is a low-boiling-point solvent having a boiling point at ambient pressure which is below 100° C, preferably below 80° C.

39. (Withdrawn) A process according to claim 38 in which the said organic solvent is selected from dichloromethane, methylene chloride, acetone, aliphatic hydrocarbons or cyclohexane.

40. (Withdrawn) A process according to claim 37 comprising a further stage d1) in which a layer of covalently bound hyaluronic acid is applied to the polymer coating of a hydrophobic nature.

41. (Withdrawn) Use of a hyaluronic acid ester for the preparation of a coating for a stent for use in angioplasty.

42. (Withdrawn) Use according to claim 41 in association with a pharmacologically active ingredient.